

PARSOL

Egenskaber	SGG PARSOL® Grøn SGG PLTH® ULTRA N	SGG PARSOL® Grå SGG PLTH® ULTRA N	SGG PARSOL® Bronze SGG PLTH® ULTRA N	SGG PLANILUX® SGG PLTH® ULTRA N
Dagslys (EN410)	6-15-6	6-15-6	6-15-6	6-15-6
Udv. reflektans LR%	9	6	7	11
Indv. reflektans LR%	11	9	9	11
Transmittans LT%	65	38	43	78
RA-indeks i %	85,7	92,8	93,9	95,0
Solenergi (EN410)				
Reflektans i %	8	11	12	21
Direkte Transmittans i %	32	27	29	50
Absorption (A1/A2) i %	55/5	55/7	51/8	18/12
g-værdi/Solfaktor	0,39	0,36	0,38	0,61
U-værdi i W/m ²				
Luft	1,4	1,4	1,4	1,4
Argon (90% 15mm afstand)	1,1	1,1	1,1	1,1
Krypton (90% 10mm afstand)	1,0	1,0	1,0	1,0

